

## Design: ALDAS

### BASIC INFORMATION

Brand	FibreGuard	Number of colour ways	38
Tariff item number	5514230000	MID	INDDEEXP16
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	22
Full roll diameter inch	8.66	Average piece length m	40
Minimum for special colour m	0	Delivery time weeks special lab dip	2

### CARE AND USAGE

#### Care codes



Care code for bleaching

Do not bleach

#### Use codes

Curtains ✓  
 Upholstery ✓  
 Accessories ✓

Curtains and draperies ✓  
 Bed covering ✓  
 Maritime

### FABRIC TYPE

There are no technical details for this section.

### ENVIRONMENTAL STANDARDS



### FR STANDARDS

BS5852 source 0  
 FMVSS 302 Pass

Yes  
 Yes

CAL 117 Complies  
 NFPA 260

Yes  
 Yes

Design: ALDAS

FABRIC SPECIFICATIONS

Composition	73% Polyester, 27% Cotton	Average yarn number	9.25
Construction	20.5x19	Woven	Yes
Useable width cm	1.38	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m <sup>2</sup>	427	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

---

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology ✓	PFC free
Other treatment	No treatment

Type of finish

---

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

---

Disperse	Reactive
Vat	Pigment

Weaving type

---

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: ALDAS

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.80
Dimensional change weft	-0.63	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.96	Dimensional change warp after ironing	-1.79
Dimensional change weft	-0.80	Dimensional change weft after ironing	-0.33
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	0.37	Dimensional change warp after ironing	0.33
Dimensional change weft	-0.10	Dimensional change weft after ironing	0.33
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	85% Polyester, 15% Cotton	Warp Is Staple	Yes
Warp Sizes	2/16	Warp Threads per cm	20.5
Warp TPM	500		

Yarn 2

Weft Composition	55% Polyester, 45% Cotton	Weft Is Staple	Yes
Weft Sizes	2/10	Weft Threads per cm	19
Weft TPM	210		