

DESIGN: **AURORE**

**BASIC INFORMATION**

|                                     |           |                              |            |
|-------------------------------------|-----------|------------------------------|------------|
| Number of colour ways               | 5         | Tariff item number           | 5309290000 |
| MID                                 | INDEEXP16 | Country of origin            | India      |
| Characteristics                     | Sheer     | Vertical repeat cm           | Stripe     |
| Vertical repeat inch                | Stripe    | Horizontal repeat cm         | 2.20       |
| Horizontal repeat inch              | 0.87      | Double folded face in        | Yes        |
| Full roll diameter cm               | 24        | Full roll diameter inch      | 9.45       |
| Average piece length m              | 50        | Minimum for special colour m | 1000       |
| Delivery time weeks special lab dip | 4         | Railroaded                   | Yes        |

**CARE AND USAGE**

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains

Yes

Curtains and draperies

Yes

**ENVIRONMENTAL STANDARDS**



GRS post-consumer



**STANDARD 100**  
2111232  
Centexbel



Certified by Control Union  
CU1036513

Yes



Prop 65

Yes

**FR STANDARDS**

FMVSS 302 Pass

No

DESIGN: **AURORE**

**FABRIC SPECIFICATIONS**

|                          |   |                     |             |
|--------------------------|---|---------------------|-------------|
| Composition              | 56% Linen, 29% Recycled Polyester, 15% Organic Cotton | Average yarn number | 24.1        |
| Construction             | 12.5x15.7   | Woven               | Yes         |
| Useable width cm         | 3.06  | Useable width inch  | 120.47      |
| Full width cm            | 308   | Full width inch     | 121.26      |
| Weight g/m <sup>2</sup>  | 117   | Thickness mm        | 0.350       |
| Colouring type           | Yarn dyed   | Filament or staple  | 100% staple |
| Textured or non textured | 100% not textured                                     |                     |             |

**Treatment**

---

No treatment Yes

**Type of finish**

---

Stenter Yes

**Weaving type**

---

Dobby Yes

**FABRIC TYPE**

There are no technical details for this section.

DESIGN: AURORE

**MECHANICAL PERFORMANCE**

|  |       |   |       |
|--|-------|---|-------|
| Colour fastness to light                                 | 6     |   |       |
| <b>Colour fastness to light - ISO 105-B02</b>            |       |   |       |
| Colour fastness to light                                 | 6     |   |       |
| <b>Colour fastness to water - ISO 105-E01</b>            |       |   |       |
| Colour fastness to water                                 | 5     |   |       |
| <b>Tearing strength - ISO 13937-3</b>                    |       |   |       |
| Tearing strength warp N                                  | 100   | Tearing strength weft N                             | 150   |
| <b>Tensile strength - ISO 13934-1</b>                    |       |   |       |
| Tensile strength warp N/5cm                              | 150   | Tensile strength weft N/5cm                         | 250   |
| <b>Elongation - ISO 13934-1</b>                          |       |   |       |
| Elongation warp %  | 20    | Elongation weft %                                   | 5.4   |
| <b>Dimensional stability (indicated in %) - ISO 3759</b> |       |   |       |
| Dimensional change warp                                  | -0.14 | Dimensional change warp after ironing with steam    | -0.33 |
| Dimensional change warp after ironing without steam      | -0.13 | Dimensional change weft                             | -0.14 |
| Dimensional change weft after ironing with steam         | 0.40  | Dimensional change weft after ironing without steam | 0.33  |

**WASHABILITY**

**Resistance to domestic washing 30° C, indicated in % - ISO 6330**

|                             |       |                                       |       |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional change warp     | -0.66 | Dimensional change warp after ironing | -0.53 |
| Dimensional change weft     | -3.00 | Dimensional change weft after ironing | -2.51 |
| Colour fastness ISO 105 C06 | 4-5   |                                       |       |

**Resistance to domestic washing 60°C, indicated in % - ISO 6330**

|                             |       |                                       |       |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional change warp     | -0.83 | Dimensional change warp after ironing | -0.33 |
| Dimensional change weft     | -3.67 | Dimensional change weft after ironing | -3.37 |
| Colour fastness ISO 105 C06 | 4-5   |                                       |       |

**Resistance to dry cleaning P, indicated in % - ISO 105 D01**

|                             |       |                                       |       |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional change warp     | -0.89 | Dimensional change warp after ironing | -0.79 |
| Dimensional change weft     | -0.90 | Dimensional change weft after ironing | -0.79 |
| Colour fastness ISO 105 D01 | 4-5   |                                       |       |

DESIGN: **AURORE**

**CONSTRUCTION**

**Yarn 1**

|                     |  |                           |        |
|---------------------|--|---------------------------|--------|
| Warp Composition    | 66% Recycled Polyester, 34% Organic Cotton | Warp Is Not High Tenacity | Yes    |
| Warp Is Staple      | Yes  | Warp Sizes                | 2,36's |
| Warp Threads per cm | 12.5                                       | Warp TPM                  | 400    |

**Yarn 2**

|                     |            |                           |      |
|---------------------|------------|---------------------------|------|
| Weft Composition    | 100% Linen | Weft Is Not High Tenacity | Yes  |
| Weft Is Staple      | Yes        | Weft Sizes                | 44/1 |
| Weft Threads per cm | 15.7       | Weft TPM                  | 400  |

**DOWNLOADS / CERTIFICATES**

There are no technical details for this section.