


## Design: Bolsa



### BASIC INFORMATION

Tariff item number	5801370000	Number of colour ways	4
Country of origin	India	MID	INDEHOM16
Vertical repeat cm	33.00	Characteristics	Velvet
Horizontal repeat cm	37.00	Vertical repeat inch	12.99
Face in	Yes	Horizontal repeat inch	14.57
Full roll diameter inch	11.81	Full roll diameter cm	30
Minimum for special colour m	1000	Average piece length m	25
Suspended box	Yes	Delivery time weeks special lab dip	4

### CARE AND USAGE

Care code comments iron on reverse side

#### Care codes

Care code for washing °C Do not wash Care code for bleaching Do not bleach



#### Use codes

Curtains  
Upholstery ✓  
Accessories ✓

Curtains and draperies  
Bed covering ✓  
Maritime

Design: Bolsa

FABRIC SPECIFICATIONS

Composition	46% Viscose, 29% Cotton, 25% Polyester	Average yarn number	12.33
Construction	31.89x22.04	Woven	Yes
Useable width cm	1.48	Useable width inch	58.27
Full width cm	150	Full width inch	59.06
Weight g/m <sup>2</sup>	614	Thickness mm	2.020
Colouring type	Yarn dyed	Filament or staple	53% staple + 47% filament
Textured or non textured	53% not textured + 47% textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo ✓	Stenter

Type of print or dye

Disperse ✓	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby
Jacquard ✓	Pile
Other	

Design: Bolsa

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



Prop 65

Yes

FR STANDARDS

BS5852 source 0  
FMVSS 302 Pass

Yes  
Yes

CAL 117 Complies  
NFPA 260

Yes  
Yes

Design: Bolsa

**MECHANICAL PERFORMANCE**

Martindale rubs	40,000	Colour fastness to light	6
Wyzenbeek double rubs	100,000	Pilling	4-5
Brush pilling	4-5	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
<b>Colour fastness to light - ISO 105-B02</b>			
Colour fastness to light	6		
<b>Colour fastness to water - ISO 105-E01</b>			
Colour fastness to water	4-5		
<b>Colour fastness to dry rub - ISO 105-X12</b>			
Colour fastness dry rub	4-5		
<b>Colour fastness to wet rub - ISO 105-X12</b>			
Colour fastness wet rub	4-5		
<b>Colour fastness to wear - ISO 12947-2</b>			
Colour fastness to wear	3-4		
<b>Tearing strength - ISO 13937-3</b>			
Tearing strength warp N	30	Tearing strength weft N	98
<b>Tensile strength - ISO 13934-1</b>			
Tensile strength warp N/5cm	1700	Tensile strength weft N/5cm	1000
<b>Elongation - ISO 13934-1</b>			
Elongation warp %	62	Elongation weft %	9.5
<b>Seam slippage - ISO 13936-2</b>			
Seam slippage warp mm	2	Seam slippage weft mm	2
<b>Dimensional stability (indicated in %) - ISO 3759</b>			
Dimensional change warp	-0.67	Dimensional change warp after ironing with steam	-0.67
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.23
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.13

Design: Bolsa

**WASHABILITY**

**Resistance to domestic washing 30° C, indicated in % - ISO 6330**

---

Dimensional change warp	-3.24	Dimensional change warp after ironing	-3.11
Dimensional change weft	-2.74	Dimensional change weft after ironing	-2.58
Colour fastness ISO 105 C06	4-5		

**Resistance to domestic washing 60° C, indicated in % - ISO 6330**

---

Dimensional change warp	-6.58	Dimensional change warp after ironing	-6.55
Dimensional change weft	-4.69	Dimensional change weft after ironing	-4.49
Colour fastness ISO 105 C06	4-5		

**Resistance to dry cleaning P, indicated in % - ISO 105 D01**

---

Dimensional change warp	-2.71	Dimensional change warp after ironing	-0.86
Dimensional change weft	-0.99	Dimensional change weft after ironing	-0.86
Colour fastness ISO 105 D01	4-5		

Design: Bolsa

**CONSTRUCTION**

**Yarn 1**

Warp Composition	100% Polyester	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Is Textured	Yes
Warp Sizes	300/288	Warp Textured	Yes
Warp Threads per cm	31.89	Warp TPM	0

**Yarn 2**

Pile Composition	100% Viscose	Pile Is Filament	Yes
Pile Is Not High Tenacity	Yes	Pile Is Textured	Yes
Pile Sizes	2/24s	Pile Textured	Yes
Pile Threads per cm	10.88	Pile TPM	0

**Yarn 3**

Weft Composition	100% Cotton	Weft Is Not High Tenacity	Yes
Weft Sizes	1/8	Weft Threads per cm	22.04
Weft TPM	0		

**Yarn 4**

Pile Composition	100% Viscose	Pile Is Not High Tenacity	Yes
Pile Is Staple	Yes	Pile Sizes	450D
Pile Threads per cm	10.88	Pile TPM	0

**DOWNLOADS / CERTIFICATES**

There are no technical details for this section.