

Design: Calango

BASIC INFORMATION

Number of colour ways	16	Tariff item number	5407920000
MID	INDDEEXP16	Country of origin	India
Characteristics	Sheer	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	29	Full roll diameter inch	11.42
Average piece length m	50	Minimum for special colour m	1000
Delivery time weeks special lab dip	2	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories

Curtains and draperies ✓
Bed covering
Maritime

ENVIRONMENTAL STANDARDS



FR STANDARDS

CANULC-S109 Large flame test	Yes	CANULC-S109 Small flame test	Yes
FMVSS 302 Pass	Yes	NFPA 701	Yes

Design: Calango

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	22.66
Construction	20.4x19.7	Woven	Yes
Useable width cm	3.00	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	177	Thickness mm	0.573
Colouring type	Piece dyed	Filament or staple	50% filament + 50% staple
Textured or non textured	68% not textured + 32% textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse ✓	Reactive
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby
Jacquard ✓	Pile
Other	

Design: Calango

MECHANICAL PERFORMANCE

Colour fastness to light	6		
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	0		
Tearing strength - ISO 13937-3			
Tearing strength warp N	130	Tearing strength weft N	37
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	270	Tensile strength weft N/5cm	720
Elongation - ISO 13934-1			
Elongation warp %	15.5	Elongation weft %	26.5
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.05	Dimensional change warp after ironing with steam	-0.33
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.08
Dimensional change weft after ironing with steam	0.80	Dimensional change weft after ironing without steam	0.20

Design: Calango

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.20	Dimensional change warp after ironing	-0.20
Dimensional change weft	-0.13	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-1.23	Dimensional change warp after ironing	-1.26
Dimensional change weft	-0.20	Dimensional change weft after ironing	0.07
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.89	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.36	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 D01	5		

Design: Calango

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	90D
Weft Threads per cm	13	Weft TPM	NA

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	9NM
Weft Textured	Yes	Weft Threads per cm	6.7
Weft TPM	500		

Yarn 3

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	550D	Warp Threads per cm	7
Warp TPM	600		

Yarn 4

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	90D
Warp Threads per cm	13.4	Warp TPM	NA

DOWNLOADS / CERTIFICATES

There are no technical details for this section.