

TECHNICAL SPECIFICATIONS SHEET

QUALITY:	EVOBASE
----------	---------

METHOD	TEST	PRODUCT PROFILE CLASSIFICATION	PASS	FAIL
ISO 12947-2: 1998 Assessment to BS 2543: 1995	Martindale abrasion	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
ISO 12945-2 : 2000 Assessment to SN 198525	Pilling on Martindale	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13936-2 Slippage	Seam slippage	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13934-1/2013	Tensile strength	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13937-3:2000	Tear strength	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 105-B02	Colour to fastness to light	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 105-X12	Colour to fastness to rubbing	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
ISO 105-E01	Colour fastness to water	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 6330:2012	Dimensional change after washing	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>

Martindale Abrasion	ISO 12947-2 : 1998 Assessment to BS 2543: 1995	
	Figured weave:	40000 rubs

Pilling on Martindale	ISO 12945-2 : 2000 Assessment to SN 198525	
	2000 cycles	3-4 grade

Seam slippage	EN ISO 13936-2 Slippage	
	Warp Slippage	Weft Slippage
	Average warp 5,4 mm	Average weft 1 mm

Tensile strength	EN ISO 13934-1:2013	Min.350N
-------------------------	---------------------	----------

Tear strength	EN ISO 13937-3:2000	Min. 20N
----------------------	---------------------	----------

Colour to fastness to light	EN ISO 105-B02	Min.5 grade
------------------------------------	----------------	-------------

Colour to fastness to rubbing	EN ISO 105-X12	
	dry	min. 3-4 grade on the greyscale
	wet	min. 3 grade on the greyscale

Colour fastness to water	ISO 105-E01	
	staining	min.3-4 grade on the greyscale
	change in colour	min.4 grade on the greyscale

Dimensional change after washing @30°C	EN ISO 6330:2012	
After washing 3 times:	Weft: max. 3%	
	Warp: max. 3%	