

## TECHNICAL SPECIFICATIONS SHEET

QUALITY:	EVOLINE
----------	---------

METHOD	TEST	PRODUCT PROFILE CLASSIFICATION	PASS	FAIL
ISO 12947-2: 1998 Assessment to BS 2543: 1995	Martindale abrasion	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
ISO 12945-2 : 2000 Assessment to SN 198525	Pilling on Martindale	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13936-2 Slippage	Seam slippage	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13934-1/2013	Tensile strength	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 13937-3:2000	Tear strength	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 105-B02	Colour to fastness to light	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 105-X12	Colour to fastness to rubbing	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
ISO 105-E01	Colour fastness to water	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>
EN ISO 6330:2012	Dimensional change after washing	General Domestic	<input checked="" type="checkbox"/>	<input type="checkbox"/>

<b>Martindale Abrasion</b>	ISO 12947-2 : 1998 Assessment to BS 2543: 1995	
	Figured weave:	60000 rubs

<b>Pilling on Martindale</b>	ISO 12945-2 : 2000 Assessment to SN 198525	
	2000 cycles	3-4 grade

<b>Seam slippage</b>	EN ISO 13936-2 Slippage									
	<table border="1" style="width: 100%;"> <tr> <td colspan="2" style="text-align: center;">Warp Slippage</td> <td colspan="2" style="text-align: center;">Weft Slippage</td> </tr> <tr> <td style="text-align: center;">Average warp</td> <td style="text-align: center;">1 mm</td> <td style="text-align: center;">Average weft</td> <td style="text-align: center;">3,6 mm</td> </tr> </table>		Warp Slippage		Weft Slippage		Average warp	1 mm	Average weft	3,6 mm
	Warp Slippage		Weft Slippage							
Average warp	1 mm	Average weft	3,6 mm							

<b>Tensile strength</b>	EN ISO 13934-1:2013	Min.350N
-------------------------	---------------------	----------

<b>Tear strength</b>	EN ISO 13937-3:2000	Min. 20N
----------------------	---------------------	----------

<b>Colour to fastness to light</b>	EN ISO 105-B02	Min.5 grade
------------------------------------	----------------	-------------

<b>Colour to fastness to rubbing</b>	EN ISO 105-X12	
	dry	min. 3-4 grade on the greyscale
	wet	min. 3 grade on the greyscale

<b>Colour fastness to water</b>	ISO 105-E01	
	staining	min.3-4 grade on the greyscale
	change in colour	min.4 grade on the greyscale

<b>Dimensional change after washing @30°C</b>	EN ISO 6330:2012	
<b>After washing 3 times:</b>	Weft: max. 3%	
	Warp: max. 3%	