

Design: GOSPEL



BASIC INFORMATION

Number of colour ways	4	Tariff item number	5407820000
MID	INDEEXP16	Country of origin	India
Characteristics	Texture	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	31	Full roll diameter inch	12.2
Average piece length m	40	Minimum for special colour m	1000
Delivery time weeks special lab dip	2	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories ✓

Curtains and draperies ✓
Bed covering
Maritime

Design: GOSPEL

FABRIC SPECIFICATIONS

Composition	81% Polyester, 19% Cotton	Average yarn number	12.32
Construction	21.3x22.8	Woven	Yes
Useable width cm	2.99	Useable width inch	117.72
Full width cm	301	Full width inch	118.5
Weight g/m ²	358	Thickness mm	0.837
Colouring type	Piece dyed	Filament or staple	61% filament + 39% staple
Textured or non textured	61% textured + 39% not textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse ✓	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: GOSPEL

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0
FMVSS 302 Pass

Yes
Yes

CAL 117 Complies
NFPA 260

Yes
Yes

Design: GOSPEL

MECHANICAL PERFORMANCE

Martindale rubs	35,000	Colour fastness to light	6
Wyzenbeek double rubs	70,000	Pilling	3-4
Brush pilling	2-3	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen medium duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	180	Tearing strength weft N	250
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1300	Tensile strength weft N/5cm	1100
Elongation - ISO 13934-1			
Elongation warp %	37	Elongation weft %	34.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	6	Seam slippage weft mm	5
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.10	Dimensional change warp after ironing with steam	-0.07
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	-0.15
Dimensional change weft after ironing with steam	0.93	Dimensional change weft after ironing without steam	0.07

Design: GOSPEL

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.10	Dimensional change warp after ironing	-0.13
Dimensional change weft	-0.27	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-0.79	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.63	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.53	Dimensional change warp after ironing	-0.66
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.66
Colour fastness ISO 105 D01	5		

Design: GOSPEL

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	450D	Warp Textured	Yes
Warp Threads per cm	21.3	Warp TPM	500

Yarn 2

Weft Composition	58% Polyester, 42% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	800D
Weft Threads per cm	11.4	Weft TPM	400

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	450D	Weft Textured	Yes
Weft Threads per cm	11.4	Weft TPM	500

DOWNLOADS / CERTIFICATES

There are no technical details for this section.