

Design: Mapale

BASIC INFORMATION

Number of colour ways	25	Tariff item number	5801360000
MID	INDEEHOM16	Country of origin	India
Characteristics	Chenille	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	32	Full roll diameter inch	0
Average piece length m	25	Minimum for special colour m	1000
Delivery time weeks special lab dip	2	Railroaded	Yes

CARE AND USAGE

Care code comments iron on reverse side

Care codes



Care code for bleaching Do not bleach

Use codes

- | | |
|---------------|--------------------------|
| Curtains ✓ | Curtains and draperies ✓ |
| Upholstery ✓ | Bed covering ✓ |
| Accessories ✓ | Maritime |

ENVIRONMENTAL STANDARDS



Prop 65 Yes

FR STANDARDS

BS5867 part 2 type B	No	BS5852 source 0	Yes
CAL 117 Complies	Yes	FMVSS 302 Pass	Yes
NFPA 260	Yes	NFPA 701	Yes

Design: Mapale

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	5.07
Construction	12.60x8.66	Woven	Yes
Useable width cm	3.05	Useable width inch	120.08
Full width cm	307	Full width inch	120.87
Weight g/m ²	419	Thickness mm	1.260
Colouring type	Piece dyed	Filament or staple	72% filament + 28% staple
Textured or non textured	72% textured + 8% not textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse ✓	Reactive
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: Mapale

MECHANICAL PERFORMANCE

Martindale rubs	20,000	Colour fastness to light	5-6
Wyzenbeek double rubs	110,000	Pilling	4-5
Brush pilling	4	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	5-6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	3-4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	150	Tearing strength weft N	210
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	720	Tensile strength weft N/5cm	430
Elongation - ISO 13934-1			
Elongation warp %	26.5	Elongation weft %	18
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	3
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.83	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	-0.20	Dimensional change weft	-0.14
Dimensional change weft after ironing with steam	-0.47	Dimensional change weft after ironing without steam	0.07

Design: Mapale

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.43	Dimensional change warp after ironing	-0.27
Dimensional change weft	-0.20	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-2.09	Dimensional change warp after ironing	-1.92
Dimensional change weft	-0.99	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-1.49	Dimensional change warp after ironing	-0.40
Dimensional change weft	-0.56	Dimensional change weft after ironing	-0.40
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Staple	Yes
Warp Sizes	6.5NM	Warp Threads per cm	12.6
Warp TPM	0		

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	6.5NM	Weft Threads per cm	8.66
Weft TPM	0		