

## Design: PICARIA



### BASIC INFORMATION

Number of colour ways	3	Tariff item number	5407615000
MID	INDDEHOM16	Country of origin	India
Characteristics	Flat Weave	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	20	Full roll diameter inch	7.87
Average piece length m	40	Minimum for special colour m	1000
Delivery time weeks special lab dip	4	Railroaded	Yes

### CARE AND USAGE

#### Care codes



Care code for bleaching

Do not bleach

#### Use codes

Curtains ✓  
Upholstery  
Accessories ✓

Curtains and draperies ✓  
Bed covering  
Maritime

Design: PICARIA

**FABRIC SPECIFICATIONS**

Composition	100% Polyester	Average yarn number	34
Construction	32.28x27.56	Woven	Yes
Useable width cm	3.07	Useable width inch	120.87
Full width cm	309	Full width inch	121.65
Weight g/m <sup>2</sup>	176	Thickness mm	0.430
Colouring type	Yarn dyed	Filament or staple	100% filament
Textured or non textured	100% not textured		

**Treatment**

---

Bio treatment	Flame retardant <input checked="" type="checkbox"/>
Soil and stain repellent	Brushed/emerised
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment

**Type of finish**

---

Calender <input checked="" type="checkbox"/>	Sanforized
Thermofixed	Washed
Airo	Stenter <input checked="" type="checkbox"/>

**Type of print or dye**

---

Disperse	Reactive
Vat	Pigment

**Weaving type**

---

Plain	Twill
Satin	Dobby
Jacquard <input checked="" type="checkbox"/>	Pile
Other	

Design: PICARIA

### FABRIC TYPE

There are no technical details for this section.

### ENVIRONMENTAL STANDARDS



### FR STANDARDS

BS5867 part 2 type B  
FMVSS 302 Pass

No  
Yes

CANULC-S109 Small flame test  
NFPA 701

No  
Yes

Design: PICARIA

**MECHANICAL PERFORMANCE**

Martindale rubs	35,000	Colour fastness to light	6
Wyzenbeek double rubs	55,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
<b>Colour fastness to light - ISO 105-B02</b>			
Colour fastness to light	6		
<b>Colour fastness to water - ISO 105-E01</b>			
Colour fastness to water	5		
<b>Colour fastness to dry rub - ISO 105-X12</b>			
Colour fastness dry rub	4-5		
<b>Colour fastness to wet rub - ISO 105-X12</b>			
Colour fastness wet rub	4-5		
<b>Colour fastness to wear - ISO 12947-2</b>			
Colour fastness to wear	4		
<b>Tearing strength - ISO 13937-3</b>			
Tearing strength warp N	85	Tearing strength weft N	52
<b>Tensile strength - ISO 13934-1</b>			
Tensile strength warp N/5cm	820	Tensile strength weft N/5cm	1400
<b>Elongation - ISO 13934-1</b>			
Elongation warp %	35.5	Elongation weft %	42
<b>Seam slippage - ISO 13936-2</b>			
Seam slippage warp mm	6	Seam slippage weft mm	5
<b>Dimensional stability (indicated in %) - ISO 3759</b>			
Dimensional change warp	-0.02	Dimensional change warp after ironing with steam	0.20
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-0.07
Dimensional change weft after ironing with steam	0.07	Dimensional change weft after ironing without steam	0.00

Design: PICARIA

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.13	Dimensional change warp after ironing	0.00
Dimensional change weft	-0.07	Dimensional change weft after ironing	-0.20
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-0.50	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.76	Dimensional change weft after ironing	-0.80
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.43	Dimensional change warp after ironing	-0.66
Dimensional change weft	-0.80	Dimensional change weft after ironing	-0.66
Colour fastness ISO 105 D01	4-5		

Design: PICARIA

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	150D
Warp Threads per cm	32.28	Warp TPM	0

Yarn 2

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	300D	Weft Threads per cm	13.78
Weft TPM	0		

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	300D
Weft Threads per cm	13.78	Weft TPM	0

DOWNLOADS / CERTIFICATES

There are no technical details for this section.