

Design: POISO

BASIC INFORMATION

Number of colour ways	30	Tariff item number	5309290000
MID	INDEEXP16	Country of origin	India
Characteristics	Sheer	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	22	Full roll diameter inch	8.7
Average piece length m	50	Minimum for special colour m	1000
Delivery time weeks special lab dip	4	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories

Curtains and draperies ✓
Bed covering
Maritime

Design: POISO

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories

Curtains and draperies ✓
Bed covering
Maritime

ENVIRONMENTAL STANDARDS



FR STANDARDS

CAL 117 Complies

Yes

Design: POISO

FABRIC SPECIFICATIONS

Composition	54% Linen, 32% Cotton, 14% Polyester	Average yarn number	25.49
Construction	13.38x13.38	Woven	Yes
Useable width cm	3.00	Useable width inch	118.11
Full width cm	302	Full width inch	118.9
Weight g/m ²	105	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized
Thermofixed	Washed
Airo	Stenter ✓

Type of print or dye

Disperse ✓	Reactive
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: POISO

MECHANICAL PERFORMANCE

Colour fastness to light	5		
Colour fastness to light - ISO 105-B02			
Colour fastness to light	5		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	64	Tearing strength weft N	40
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	310	Tensile strength weft N/5cm	450
Elongation - ISO 13934-1			
Elongation warp %	19	Elongation weft %	5.8
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.10	Dimensional change warp after ironing with steam	0.00
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	-0.15
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	0.00

Design: POISO

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.27	Dimensional change warp after ironing	-0.20
Dimensional change weft	-4.23	Dimensional change weft after ironing	-2.50
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-1.60	Dimensional change warp after ironing	-1.27
Dimensional change weft	-6.59	Dimensional change weft after ironing	-6.13
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.93	Dimensional change warp after ironing	-1.26
Dimensional change weft	-1.56	Dimensional change weft after ironing	-1.26
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Weft Composition	100% Linen	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	44 les linen dyed
Weft Threads per cm	13.38		

Yarn 2

Warp Composition	30% Polyester, 70% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/36 PC Linen Dyed
Warp Threads per cm	13.38		