

## TECHNICAL FABRIC DETAILS

# TERRACE



Terrace is an outdoor fabric with a more classic and familiar plaid pattern. Terrace invokes rural, agricultural environments where farmers would work the land in the typical plaid shirt. An ideal fabric for those who don't want to distance themselves from a traditional world and feel the warmth of the earth in space.



## Article specification

Width	160 cm
Horizontal repeat cm	5 cm
Vertical repeat cm	5 cm
Composition	100% SOLUTION DYED ACRYLIC
Weight	280 gr/m <sup>2</sup>
Thickness (mm)	

## Cleaning Instructions



## Use Code

Upholstery  
Accessories  
Curtains  
Outdoor / Indoor  
Nautic  
Contract

## Environmental Standards

## FR Standards

# Finish

Water repellent

Anti-stain treatment

# Optional Fabric Treatment

Waterproof/ Impermeable ( Water Column: 1000 mm): Minimum one piece

Extra Softness + Martindale (Higher Resistance): Minimum one piece

Fireproof Treatment (UNE 1021 Parts 1-2/ IMO Pef 2010 Anex.1 Part 8/ BS5252 Cigarette & Match) : Minimum 500 meters

# Warranty: 5 Years

The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations.

Waterproof and flame retardant treatments: Recommended for cushions and upholstery only. Always use the lamination face inside. Do not expose the coated side to sun or light.

# Mechanical Performance

Abrasion Test / Martindale Rubs (EN ISO 12947-1,2)	20.000
Piling Test (EN ISO 12945-2)	4-5 / 5
Colour Fastness to light (ISO 105-B02-2)	7/8
Colour fastness to dry rub ( EN ISO 105-X12)	4-5 / 5
Tearing strength (ISO 13934-1)	Warp: 170 N Weft: 150 N
Tensile Strenght (EN ISO 13934-1)	Warp: 1900 N Weft: 1950 N
Colour fastness to artificial weathering (ISO 105-B04)	4/5
Seam slippage (ISO 13936-2)	Warp: 5.0 mm Weft: 3.0 mm
Colour fastness to chlorinated water (ISO 105-E03)	5/5
Ultraviolet protection factor UPF (AZ/NZS 4399/1996)	50+
Spray test (ISO 24920)	5/5
Shrinkage to washing (ISO 5077:2007)	Warp: -1.5% Weft: 0%
Water column mm (ISO 20811)	100